

OK Autrod 13.64

Low-alloyed and Ti-B micro-alloyed, copper-coated solid wire for Submerged Arc Welding. Especially for high dilution welds where low temperature impact toughness properties are required. For fine grained steels, pipeline steels, ship building steels, etc.

Dane techniczne	
Klasyfikacje	SFA/AWS A5.23 : EA2TiB EN ISO 14171-A : S2MoTiB
Aprobaty	VdTÜV : 12103

Zatwierdzenia s oparte na lokalizacji fabryki. Aby uzyska wiecej informacji, skontaktuj si z ESAB.

Skad drutu %					
C	Mn	Si	Mo	Ti	B
0.07	1.22	0.28	0.49	0.14	0.013