

OK Autrodur 38 G M

A copper coated, low-alloyed solid GMAW wire used for hard facing and building up, giving a wear resistant weld metal with a hardness between 35-40 HRC. Used for repair and maintenance of e.g. tracks, rails, wheels, rolls, railcrossings, shafts, shovel teeth and other parts on digging machines, tools like dies etc.

Specifications

Classifications	EN 14700 : Fe2
Approvals	NAKS/HAKC : 1.2mm

Approvals are based on factory location. Please contact ESAB for more information.

Alloy Type	Low alloyed (0.7 C, 2 % Mn, 1 % Cr, 0.2 % Ti)
Shielding Gas	M12, M21, C1 (EN ISO 14175)

Typical Weld Metal Analysis %

C	Mn	Si	S	P	Cr	Ti
Shielding gas;80Ar/20CO2						
0.6	1.4	0.4	0.01	0.01	1.0	0.06
Shielding gas;CO2						
0.6	1.0	0.2	0.01	0.01	1.0	0.05

Typical Wire Composition %

C	Mn	Si	Cr	Ti
0.69	1.92	0.49	1.00	0.2

Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
1.2 mm (0.047 in.)	120-350 A	20-33 V	2.7-12.4 m/min (106-488 in./min)	1.5-6.6 kg/h (3.3-14. lbs/h)